

5268
10.0
= 5268

NATIONAL BUREAU OF STANDARDS REPORT

5268

THE OBSERVED NATURE OF IGNITION AND BURNING
OF
TWO SOLID PROPELLANTS AT PRESSURES BELOW ONE ATMOSPHERE

by

T. G. Lee



U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

THE NATIONAL BUREAU OF STANDARDS

Functions and Activities

The functions of the National Bureau of Standards are set forth in the Act of Congress, March 3, 1901, as amended by Congress in Public Law 619, 1950. These include the development and maintenance of the national standards of measurement and the provision of means and methods for making measurements consistent with these standards; the determination of physical constants and properties of materials; the development of methods and instruments for testing materials, devices, and structures; advisory services to Government Agencies on scientific and technical problems; invention and development of devices to serve special needs of the Government; and the development of standard practices, codes, and specifications. The work includes basic and applied research, development, engineering, instrumentation, testing, evaluation, calibration services, and various consultation and information services. A major portion of the Bureau's work is performed for other Government Agencies, particularly the Department of Defense and the Atomic Energy Commission. The scope of activities is suggested by the listing of divisions and sections on the inside of the back cover.

Reports and Publications

The results of the Bureau's work take the form of either actual equipment and devices or published papers and reports. Reports are issued to the sponsoring agency of a particular project or program. Published papers appear either in the Bureau's own series of publications or in the journals of professional and scientific societies. The Bureau itself publishes three monthly periodicals, available from the Government Printing Office: The Journal of Research, which presents complete papers reporting technical investigations; the Technical News Bulletin, which presents summary and preliminary reports on work in progress; and Basic Radio Propagation Predictions, which provides data for determining the best frequencies to use for radio communications throughout the world. There are also five series of nonperiodical publications: The Applied Mathematics Series, Circulars, Handbooks, Building Materials and Structures Reports, and Miscellaneous Publications.

Information on the Bureau's publications can be found in NBS Circular 460. Publications of the National Bureau of Standards (\$1.25) and its Supplement (\$0.75), available from the Superintendent of Documents, Government Printing Office, Washington 25, D. C.

Inquiries regarding the Bureau's reports should be addressed to the Office of Technical Information, National Bureau of Standards, Washington 25, D. C.

NATIONAL BUREAU OF STANDARDS REPORT

NBS PROJECT

1002-30-4873

NBS REPORT

5268

May 2, 1957

THE OBSERVED NATURE OF IGNITION AND BURNING OF

TWO SOLID PROPELLANTS AT PRESSURES BELOW ONE ATMOSPHERE

by
T. G. Lee

for
Bureau of Ships
Department of the Navy

Code 538

Index Number NS-183-001

IMPORTANT NOTICE

NATIONAL BUREAU OF STANDARDS
intended for use within the Government
to additional evaluation and revision
listing of this Report, either in
the Office of the Director, National
however, by the Government agency
to reproduce additional copies.

Approved for public release by the
Director of the National Institute of
Standards and Technology (NIST)
on October 9, 2015.

Progress accounting documents
already published it is subjected
production, or open-literature
information is obtained in writing from
such permission is not needed,
prepared if that agency wishes



U. S. DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS

THE OBSERVED NATURE OF IGNITION AND BURNING
OF
TWO SOLID PROPELLANTS AT PRESSURES BELOW ONE ATMOSPHERE

ABSTRACT

Experimental observations are reported on the burning characteristics of a double base and a composite propellant under low ambient pressure conditions.

INTRODUCTION

The theory of the influence of pressure on burning rate of solid propellants has been given considerable attention (1). Generally, however, data are available only for pressures normally found inside rocket motors and ballistic chambers. If one extrapolates these pressure-burning rate data to zero pressure, a finite burning rate is found, although propellants cease to burn at higher pressures. Thus, it was shown by Huggett (1) that such extrapolation is not valid. Very little unclassified data are available on propellant burning rates at reduced pressure. The present work was undertaken to determine experimentally a pressure below which self-sustaining combustion of a small sample of a given propellant would not be maintained in an ambient atmosphere at 75°F. We shall call that pressure the "maximum quenching pressure." Two types of propellant, supplied by the Navy, were investigated, Double Base Navy Mark-32 and a composite propellant containing 82 percent KClO_4 , NH_4ClO_4 , and 18 percent Polyurethane. The pressure region investigated was between 10 mm and 760 mm Hg absolute. Some information on the combustion behavior of the propellants near the region of maximum quenching pressure and its dependence on propellant composition was also obtained.

Ignition and combustion of propellants are governed by energy balance relations (2). Ignition occurs when a small volume of the propellant is raised to a temperature at which the rate of heat generation by exothermic

reaction exceeds the rate of heat loss by conduction, convection, and radiation. Quenching or extinction of a burning propellant will occur if the reverse of the above case is true. At reduced pressure (generally below atmospheric) high heat loss is caused by diffusion of hot gaseous reaction products and reacting vapor away from the fizz zone. This reduces the rate of decomposition or melting in the subsurface zone and finally results in quenching.

The maximum quenching pressure appears to be influenced by propellant composition, including stabilizer and coolant, as well as by specimen configuration. For composite propellants, the type of matrix (binder) and the particle size of the filler are also important factors (3).

EXPERIMENTAL PROCEDURES

The experiment was designed to observe the nature of ignition, combustion, and quenching at reduced pressures ranging from 10 mm to 760 mm Hg absolute and a ambient temperature of 75°F for a Double Base Propellant-Navy Mark-32 and a composite propellant consisting mainly of potassium and ammonium perchlorate filler and polyurethane matrix.

Electrically heated 26 gauge Nichrome resistance wire, 3 cm long, was used as the ignition source. The wire was inserted through a hole in the center along the short axis of a specimen 2 mm thick, in the shape of an equilateral triangle 7 mm on a side. To prevent subsequent sliding, the wire was slightly bent downward at the middle where the specimen rested. The ends of the wire were connected to two electrode clips suspended in a 7 liter vacuum jar. The jar could be evacuated to any desired pressure down to about 10 mm Hg absolute. The power supplied to the ignition wire, about 4 watts, was sufficient to make the wire red hot.

Depending on the pressure condition, the hot wire would cause melting, decomposition, slow combustion or ignition of the propellant at the surface of contact with the wire. In the non-ignition cases, slow decomposition or melting next to the hot wire would gradually increase the diameter of the hole in the propellant. As a result of the weight of the specimen, a slot would be formed in the specimen by the hot wire, allowing it to drop from the wire. Then all activity would cease. If the pressure

in the jar were slightly higher than the maximum quenching pressure, the specimen would continue its slow combustion or decomposition after the drop, as evidenced by fuming or generation of white or brown smoke. At a still higher pressure, with double base propellant there was spark burning but no visible flame. In this case small glowing particles were ejected from the burning propellant.

Table 1 is a summary of the results obtained. It is based on a limited number of runs, 30 runs were made for the two types of propellant. The indicated pressure ranges are only approximate, since only gradual transition from one mechanism to the other was observed. For the double base propellant, the pressure rise was less than 5 percent above the initial absolute pressure. The composite propellant produced somewhat higher pressures.

CONCLUSIONS

For the two propellants tested, there exist maximum quenching pressures below which all specimens were quenched. Such quenching pressures probably depend primarily on the composition of the propellant, but experimental conditions such as specimen configuration, size, ignition-wire temperature and contact area may influence the quenching pressure observed.

The quenching pressure range for the Double Base, Mark-32 propellant was between 300 and 400 mm Hg absolute. For the composite propellant of $\text{KClO}_4\text{-NH}_4\text{ClO}_4\text{-polyurathane}$, it was between 40 and 50 mm Hg absolute.

Additional work should be done to determine the maximum quenching pressure for other propellants and the effect of specimen size and configuration on quenching pressure before any general conclusions can be drawn.

Table 1. Observed Nature of Ignition and Burning of Two Propellants at Reduced Pressures

Double Base Mark-32		Composite - $\text{KClO}_4\text{-NH}_4\text{ClO}_4$ Polyurethane	
Pressure mm Hg abs		Pressure mm Hg abs	
10 to 200	No ignition. Fuming at contact surfaces. Immediate quenching after specimen dropped from wire.	10 to 50	No ignition. Fuming at contact surface. Immediate quenching after specimen dropped from wire.
200 to 300	Same as above, except larger slot produced in specimen.	50 to 120	Ignited slowly. Continued slow burning after drop. Specimen consumed.
300 to 400	Spark burning at contact surface. Quenching after drop.	120 to 300	Ignited more readily. Continued burning after drop. Specimen consumed.
400 to 500	Spark burning at contact surface. Momentarily burning after drop.	300 to 760	Immediate ignition, bright flame, fast burning. Specimen consumed.
500 to 600	Slow flame-type burning before and after drop. Specimen consumed.		
600 to 760	Immediate ignition, bright flame, fast burning. Specimen consumed.		

REFERENCES

- (1) Lewis, B., Pease, R. N., Taylor, H. S., Editors, High Speed Aerodynamics and Jet Propulsion, Vol. II, Combustion Processes, Princeton University Press, 1956.
- (2) Altman, David, and Grant, A. F., Jr., Thermal Theory of Solid Propellant Ignition by Hot Wire, Fourth Symposium on Combustion, William and Wilkin Co., Baltimore, Maryland, 1953.
- (3) Crawford, B. L., et al. Study on Propellants, Office of Scientific Research and Development Report 6374, 1945.

U. S. DEPARTMENT OF COMMERCE

Sinclair Weeks, *Secretary*

NATIONAL BUREAU OF STANDARDS

A. V. Astin, *Director*



THE NATIONAL BUREAU OF STANDARDS

The scope of activities of the National Bureau of Standards at its headquarters in Washington, D. C., and its major field laboratories in Boulder, Colorado, is suggested in the following listing of the divisions and sections engaged in technical work. In general, each section carries out specialized research, development, and engineering in the field indicated by its title. A brief description of the activities, and of the resultant reports and publications, appears on the inside front cover of this report.

WASHINGTON, D. C.

Electricity and Electronics. Resistance and Reactance. Electron Tubes. Electrical Instruments. Magnetic Measurements. Dielectrics. Engineering Electronics. Electronic Instrumentation. Electrochemistry.

Optics and Metrology. Photometry and Colorimetry. Optical Instruments. Photographic Technology. Length. Engineering Metrology.

Heat and Power. Temperature Physics. Thermodynamics. Cryogenic Physics. Rheology and Lubrication. Engine Fuels.

Atomic and Radiation Physics. Spectroscopy. Radiometry. Mass Spectrometry. Solid State Physics. Electron Physics. Atomic Physics. Nuclear Physics. Radioactivity. X-rays. Betatron. Nucleonic Instrumentation. Radiological Equipment. AEC Radiation Instruments.

Chemistry. Organic Coatings. Surface Chemistry. Organic Chemistry. Analytical Chemistry. Inorganic Chemistry. Electrodeposition. Gas Chemistry. Physical Chemistry. Thermochemistry. Spectrochemistry. Pure Substances.

Mechanics. Sound. Mechanical Instruments. Fluid Mechanics. Engineering Mechanics. Mass and Scale. Capacity, Density, and Fluid Meters. Combustion Controls.

Organic and Fibrous Materials. Rubber. Textiles. Paper. Leather. Testing and Specifications. Polymer Structure. Organic Plastics. Dental Research.

Metallurgy. Thermal Metallurgy. Chemical Metallurgy. Mechanical Metallurgy. Corrosion. Metal Physics.

Mineral Products. Engineering Ceramics. Glass. Refractories. Enameled Metals. Concreting Materials. Constitution and Microstructure.

Building Technology. Structural Engineering. Fire Protection. Heating and Air Conditioning. Floor, Roof, and Wall Coverings. Codes and Specifications.

Applied Mathematics. Numerical Analysis. Computation. Statistical Engineering. Mathematical Physics.

Data Processing Systems. SEAC Engineering Group. Components and Techniques. Digital Circuitry. Digital Systems. Analogue Systems. Application Engineering.

• Office of Basic Instrumentation

• Office of Weights and Measures

BOULDER, COLORADO

Cryogenic Engineering. Cryogenic Equipment. Cryogenic Processes. Properties of Materials. Gas Liquefaction.

Radio Propagation Physics. Upper Atmosphere Research. Ionospheric Research. Regular Propagation Services. Sun-Earth Relationships.

Radio Propagation Engineering. Data Reduction Instrumentation. Modulation Systems. Navigation Systems. Radio Noise. Tropospheric Measurements. Tropospheric Analysis. Radio Systems Application Engineering.

Radio Standards. Radio Frequencies. Microwave Frequencies. High Frequency Electrical Standards. Radio Broadcast Service. High Frequency Impedance Standards. Calibration Center. Microwave Physics. Microwave Circuit Standards.

